



GX7CrNiMo12-1 (EN 1.4008) Martensitic Stainless Steel Casting Material

Introduction

GX7CrNiMo12-1 is a martensitic stainless steel grade specified in EN 10283 for corrosion-resistant cast components. Casting process options include Investment Casting, Shell Molding Casting and Sand Casting, subject to the applicable specification and component requirements.

Manufacturing Process

Investment Casting
Shell Molding Casting
Sand Casting

Equivalent Grades

N/A

Reference Standards

Standard	Standard Title	Edition	Specification	Identifier
EN 10283	Corrosion resistant steel castings	2019	GX7CrNiMo12-1	EN 1.4008
ISO 11972	Corrosion-resistant cast steels for general applications	2023	GX7CrNiMo12-1	EN 1.4008

Physical Properties

EN 10283–2019

Property	Value	Note
Density	7.7 kg/dm ³	Test at 20 °C
Specific Heat	460 J/(kg·K)	Test at 20 °C
Thermal Conductivity	25 W/(m·K)	Test at 50 °C
Thermal Conductivity	26 W/(m·K)	Test at 100 °C
Thermal Expansion	10.5 ×10 ⁻⁶ /K	Temperature range: 20–100 °C
Thermal Expansion	11.3 ×10 ⁻⁶ /K	Temperature range: 20–300 °C
Thermal Expansion	12 ×10 ⁻⁶ /K	Temperature range: 20–500 °C

Chemical Composition



Element	EN 10283 Edition 2019 · wt.% Cast analysis	ISO 11972 Edition 2023 · wt.%
C	≤ 0.10	≤ 0.10
Si	≤ 1.00	≤ 1.0
Mn	≤ 1.00	≤ 1.0
P	≤ 0.035	≤ 0.035
S	≤ 0.025	≤ 0.025
Cr	12.00–13.50	12.0–13.5
Ni	1.00–2.00	1.0–2.0
Mo	0.20–0.50	0.20–0.50
Cu	≤ 0.30 ^[1]	— / Not specified
V	≤ 0.08 ^[1]	— / Not specified

Notes

EN 10283 · Edition 2019

^[1] Cu/V: Applies unless otherwise agreed; unspecified elements shall not be intentionally added without purchaser agreement except for finishing the heat.

Heat Treatment

EN 10283–2019 · +QT

Step	Operation	Temperature	Cooling
1	quenching	1000–1050 °C	air or liquid
2	tempering	620–720 °C	—

ISO 11972–2023 · Heat treated

Step	Operation	Temperature	Cooling
1	austenitizing	1000–1050 °C	air cool
2	tempering	620–720 °C	air or furnace cool

Mechanical Properties

Property	EN 10283 Edition 2019 ^[1]	ISO 11972 Edition 2023 ^[2]
Yield Strength (Rp0.2)	≥ 440 MPa	≥ 440 MPa
Tensile Strength	≥ 590 MPa	≥ 590 MPa



Property	EN 10283 Edition 2019 ^[1]	ISO 11972 Edition 2023 ^[2]
Elongation	$\geq 15 \%$	$\geq 15 \%$
Impact Energy	$\geq 27 \text{ J}^{[3]}$	$\geq 27 \text{ J}^{[4]}$

Notes

EN 10283 · Edition 2019

^[1] All properties in this column: wall thickness $\leq 300 \text{ mm}$; Test block; maximum thickness 150 mm; Room temperature; Yield and tensile strength also apply to the casting up to the maximum specified wall thickness.

^[3] Impact Energy: KV2 as specified in

ISO 11972 · Edition 2023

^[2] All properties in this column: wall thickness $\leq 300 \text{ mm}$; Room temperature; Test blocks used to verify mechanical properties shall not exceed 150 mm thickness. Properties for samples removed from castings shall be agreed between manufacturer and purchaser.

^[4] Impact Energy: Verification of impact tests is required only when indicated by the customer.

Welding Conditions

EN 10283–2019

Requirement	Value
Preheat	150–200 °C ^[1]
Interpass Temperature	$\leq 300 \text{ °C}$
Post-weld Heat Treatment	Tempering at the same temperature as the base material ^[2]
Post-weld Heat Treatment	Tempering at the same temperature as the base material ^[3]

Notes

EN 10283 · Edition 2019

^[1] Preheat: Preheat depends on casting geometry, thickness and climatic conditions.

^[2] Post-weld Heat Treatment: minor welds

^[3] Post-weld Heat Treatment: major welds

Applications

Typical casting applications include impellers, pump parts and valve parts exposed to water or steam.

Last Updated: 2026-10-16



Casting Quality Industrial

As a professional manufacturer in China, We Casting Quality focus on Metal Parts OEM industry, and provide solutions and services in Metal Casting field as following:

Sand Casting

Investment Casting, Lost Wax process

Shell Casting

Lost Form Casting

Permanent Mold Casting

CNC Machining

CAD Design

Tools/Mold Design

Material Supplied

Cast Iron Castings (Grey Iron, Malleable Iron, Ductile Iron)

Carbon Steel and Alloy Steel Castings

Stainless Steel and Duplex Stainless Steel Castings

Aluminum Castings

Bronze and Brass Castings

Titanium and Cobalt Alloy Castings

What We Can Do

Design Ability

Our engineers will help you to improve the designs based on casting technology, then The simulation software will be processed to verify the casting pouring system. Pro/E, Solidworks, AutoCAD and ProCast are available in Casting Quality Industrial.

Saving Cost

Some manufacture processes may lead high cost. We will analyses the designs and advise the suitable methods to our customers. The best solution will be adopted.

Quality Control

From the raw material selecting to bulk production processing, all procedures will follow PPAP program if necessary. The certificates will be provided including chemistry, hardness, mechanical property or NDT testing.

Production Capacity

The max iron/steel castings can reach 30tons in weight, meanwhile the minus casting is around 1gram only.

We also have prototyping and 3D scanning ability for sample plan.

Logistic Service

The products will be delivered directly to customer's workshop, which will save plenty of work for clients.

Contact with Us Immediately:

Mark Wang

Email: mark@castingquality.com

WhatsApp: +861396488078

Website: www.castingquality.com