



## G-NiCr15 (EN 2.4815) Nickel-Chromium Alloy Casting Material

### Introduction

G-NiCr15 is a nickel-chromium heat-resistant casting alloy covered by EN 10295. Casting production and service suitability must follow the applicable specification and component requirements. CQ-approved manufacturing options are Sand Casting and Investment Casting.

### Manufacturing Process

Sand Casting  
Investment Casting

### Equivalent Grades

N/A

### Reference Standards

| Standard | Standard Title                | Edition | Specification | Identifier |
|----------|-------------------------------|---------|---------------|------------|
| EN 10295 | Heat resistant steel castings | 2002    | G-NiCr15      | —          |

### Physical Properties

N/A

### Chemical Composition

| Element | EN 10295<br>Edition 2002 · wt.%<br>Cast analysis |
|---------|--------------------------------------------------|
| C       | 0.35–0.65                                        |
| Si      | 1.00–2.50                                        |
| Mn      | ≤ 2.00                                           |
| P       | ≤ 0.040                                          |
| S       | ≤ 0.030                                          |
| Cr      | 12.00–18.00                                      |
| Ni      | 58.00–66.00                                      |
| Fe      | balance                                          |
| Mo      | ≤ 1.00                                           |
| Co      | ≤ 1.00 <sup>[1]</sup>                            |
| W       | ≤ 0.60 <sup>[1]</sup>                            |
| Nb      | ≤ 0.60 <sup>[1]</sup>                            |



| Element | EN 10295<br>Edition 2002 · wt.%<br>Cast analysis |
|---------|--------------------------------------------------|
| Cu      | $\leq 0.25^{[1]}$                                |

## Notes

### EN 10295 · Edition 2002

<sup>[1]</sup> Co/W/Nb/Cu: Unless otherwise agreed: limit for element unspecified in; no intentional addition except for finishing the heat.

## Heat Treatment

NO HEAT TREATMENT

## Mechanical Properties

| Property         | EN 10295<br>Edition 2002 <sup>[1]</sup> |
|------------------|-----------------------------------------|
| Yield Strength   | $\geq 200$ MPa                          |
| Tensile Strength | $\geq 400$ MPa                          |
| Elongation       | $\geq 3$ %                              |

## Notes

### EN 10295 · Edition 2002

<sup>[1]</sup> All properties in this column: Room temperature

## Welding Conditions

N/A

## Applications

At the nickel-chromium heat-resistant casting-family level, typical applications include custom cast components for elevated-temperature industrial service; selection must account for the specified service environment.

Last Updated: 2026-10-13



## Casting Quality Industrial

As a professional manufacturer in China, We Casting Quality focus on Metal Parts OEM industry, and provide solutions and services in Metal Casting field as following:

Sand Casting

Investment Casting, Lost Wax process

Shell Casting

Lost Form Casting

Permanent Mold Casting

CNC Machining

CAD Design

Tools/Mold Design

### Material Supplied

Cast Iron Castings (Grey Iron, Malleable Iron, Ductile Iron)

Carbon Steel and Alloy Steel Castings

Stainless Steel and Duplex Stainless Steel Castings

Aluminum Castings

Bronze and Brass Castings

Titanium and Cobalt Alloy Castings

### What We Can Do

#### Design Ability

Our engineers will help you to improve the designs based on casting technology, then The simulation software will be processed to verify the casting pouring system. Pro/E, Solidworks, AutoCAD and ProCast are available in Casting Quality Industrial.

#### Saving Cost

Some manufacture processes may lead high cost. We will analyses the designs and advise the suitable methods to our customers. The best solution will be adopted.

#### Quality Control

From the raw material selecting to bulk production processing, all procedures will follow PPAP program if necessary. The certificates will be provided including chemistry, hardness, mechanical property or NDT testing.

#### Production Capacity

The max iron/steel castings can reach 30tons in weight, meanwhile the minus casting is around 1gram only.

We also have prototyping and 3D scanning ability for sample plan.

#### Logistic Service

The products will be delivered directly to customer's workshop, which will save plenty of work for clients.

#### Contact with Us Immediately:

Mark Wang

Email: [mark@castingquality.com](mailto:mark@castingquality.com)

WhatsApp: +861396488078

Website: [www.castingquality.com](http://www.castingquality.com)