ISO1083/JS/350-22-RT Ductile Cast Iron Casting Material

Introduction

ISO1083/JS/350-22-RT is a ductile iron casting grade covered by ISO 1083. Its graphite is mainly spheroidal, in forms V and VI. The wider ductile-iron family is used for pump casings and machinery housings. Impact properties apply when testing is specified at order acceptance.

Manufacturing Process

Sand Casting
Shell Molding Casting
Lost Foam Casting

Equivalent Materials

Standard	Material Grade
EN 1563	EN-GJS-350-22-RT
GB/T 1348	QT350-22R

Approximate materials; not guaranteed interchangeable.

Reference Standards

Standard	Standard Title	Edition	Specification
ISO 1083	Spheroidal graphite cast irons — Classification	2018	ISO1083/JS/350-22-RT

Physical Properties

Not Available

Chemical Composition

Not Available

Heat Treatment

ISO 1083–2018

Not Available

Mechanical Properties

Primary Mechanical Properties

ISO 1083 — 2018

Condition: Castings-cut specimen, 30 < t <= 60; 30 < t <= 60 mm

Informative

Property	Value
Yield Strength (Rp0.2)	>= 210 MPa
Tensile Strength	>= 320 MPa
Elongation	>= 15 %

Test pieces machined from samples cut from castings
ISO1083/JS/350-22C-RT/C
Project owner confirmed mapping to ISO1083/JS/350-22-RT and /C sample-cut-from-casting meaning original source designation retained.
Informative reference value
not an acceptance requirement
Elongation: For elongation results, the reference gauge length is L0 = 5 d.

ISO 1083 — 2018

Condition: Castings-cut specimen, 60 < t <= 200; 60 < t <= 200 mm
Informative

Property	Value
Yield Strength (Rp0.2)	>= 200 MPa
Tensile Strength	>= 310 MPa
Elongation	>= 12 %

Test pieces machined from samples cut from castings
ISO1083/JS/350-22C-RT/C
Project owner confirmed mapping to ISO1083/JS/350-22-RT and /C sample-cut-from-casting meaning original source designation retained.
Informative reference value
not an acceptance requirement
Elongation: For elongation results, the reference gauge length is L0 = 5 d.

ISO 1083 — 2018

Condition: Castings-cut specimen, t <= 30; t <= 30 mm
Informative

Property	Value
Yield Strength (Rp0.2)	>= 220 MPa
Tensile Strength	>= 340 MPa
Elongation	>= 20 %

Test pieces machined from samples cut from castings
ISO1083/JS/350-22C-RT/C
Project owner confirmed mapping to ISO1083/JS/350-22-RT and /C sample-cut-from-casting meaning original source designation retained.

Informative reference value

not an acceptance requirement

Elongation: For elongation results, the reference gauge length is L0 = 5 d.

ISO 1083 — 2018

Property	t <= 30 mm	30 < t <= 60 mm	60 < t <= 200 mm
Yield Strength (Rp0.2)	>= 220 MPa	>= 220 MPa	>= 210 MPa
Tensile Strength	>= 350 MPa	>= 330 MPa	>= 320 MPa
Elongation	>= 22 %	>= 18 %	>= 15 %

Values apply to sand moulds or moulds of comparable thermal behaviour

alternative processes are subject to amendments agreed in the order.

Separately cast, cast-on or side-by-side cast samples

Elongation: Elongation values determined from L0 = 5 d

Elongation: other gauge lengths see 9.1 and Annex B.

ISO 1083 — 2018

Condition: mean of three: 23 ± 5 °C

Property	t <= 30 mm	30 < t <= 60 mm	60 < t <= 200 mm
Impact Energy	>= 17 J	>= 17 J	>= 15 J

Values apply to sand moulds or moulds of comparable thermal behaviour

alternative processes are subject to amendments agreed in the order.

V-notched

machined from cast samples

Mean of three

Impact energy is determined only if specified by the purchaser by acceptance of the order.

ISO 1083 — 2018

Condition: individual minimum: 23 ± 5 °C

Property	t <= 30 mm	30 < t <= 60 mm	60 < t <= 200 mm
Impact Energy	>= 14 J	>= 14 J	>= 12 J

Values apply to sand moulds or moulds of comparable thermal behaviour

alternative processes are subject to amendments agreed in the order.

V-notched

machined from cast samples

Individual minimum

Impact energy is determined only if specified by the purchaser by acceptance of the order.

Welding Conditions

Not Available

Applications

Ductile iron ISO1083/JS/350-22-RT belongs to the spheroidal graphite iron casting family. Family-level examples include cast valve bodies, pump housings, bearing housings and covers used in mechanical assemblies. These types of components occur in agricultural machinery, construction equipment and industrial fluid-handling systems. ISO 1083 notes that this grade can be suitable for some pressure-vessel applications; the relevant component requirements still apply.

CASTING QUALITY

Last Updated: 2026-11-16

Casting Quality Industrial

As a professional manufacturer in China, We Casting Quality focus on Metal Parts OEM industry, and provide solutions and services in Metal Casting field as following:

Sand Casting

Investment Casting, Lost Wax process

Shell Casting

Lost Form Casting

Permanent Mold Casting

CNC Machining

CAD Design

Tools/Mold Design

Material Supplied

Cast Iron Castings (Grey Iron, Malleable Iron, Ductile Iron)

Carbon Steel and Alloy Steel Castings

Stainless Steel and Duplex Stainless Steel Castings

Aluminum Castings

Bronze and Brass Castings

Titanium and Cobalt Alloy Castings

What We Can Do

Design Ability

Our engineers will help you to improve the designs based on casting technology, then The simulation software will be processed to verify the casting pouring system. Pro/E, Solidworks, AutoCAD and ProCast are available in Casting Quality Industrial.

Saving Cost

Some manufacture processes may lead high cost. We will analyses the designs and advise the suitable methods to our customers. The best solution will be adopted.

Quality Control

From the raw material selecting to bulk production processing, all procedures will follow PPAP program if necessary. The certificates will be provided including chemistry, hardness, mechanical property or NDT testing.

Production Capacity

The max iron/steel castings can reach 30tons in weight, meanwhile the minus casting is around 1gram only.

We also have prototyping and 3D scanning ability for sample plan.

Logistic Service

The products will be delivered directly to customer’s workshop, which will save plenty of work for clients.

Contact with Us Immediately:

Mark Wang

Email: mark@castingquality.com

WhatsApp: +861396488078

Website: www.castingquality.com

CASTING QUALITY