ISO1083/JS/550-5 Ductile Cast Iron Casting Material

Introduction

ISO1083/JS/550-5 is an ISO 1083 ductile iron for castings. The standard reports ferrite-pearlite as a typical matrix. Family applications include hubs and gears in agricultural and industrial machinery.

Manufacturing Process

Sand Casting
Shell Molding Casting
Lost Foam Casting

Equivalent Materials

Standard	Material Grade
SAE J434	D550
ASTM A536	80-55-06
GB/T 1348	QT550-5

Approximate materials; not guaranteed interchangeable.

Reference Standards

Standard	Standard Title	Edition	Specification
ISO 1083	Spheroidal graphite cast irons — Classification	2018	ISO1083/JS/550-5

Physical Properties

Property	Value	Applicable Conditions
Density	7.1 kg/dm3	Room temperature unless otherwise specified
Elastic Modulus	172 GN/m2	Room temperature unless otherwise specified
Poisson Ratio	0.275	Room temperature unless otherwise specified
Thermal Conductivity	34 W/(m·K)	Test temperature: 300 °C
Specific Heat	515 J/(kg·K)	Temperature range: 20–500 °C
Thermal Expansion	12.5 um/(m·K)	Temperature range: 20–400 °C
Electrical Resistivity	0.52 uohm·m	Room temperature unless otherwise specified
Hysteresis Loss	1800 J/m3	Hysteresis loss at B = 1 T; Room temperature unless otherwise specified

Property	Value	Applicable Conditions
Matrix Structure	ferrite-pearlite	
Maximum Magnetic Permeability	1200 uH/m	Room temperature unless otherwise specified

Sources: ISO 1083:2018

Matrix Structure: Typical structure.

Informative values; not mandatory acceptance limits.

Chemical Composition

Not Available

Heat Treatment

ISO 1083–2018

Not Available

Mechanical Properties

Primary Mechanical Properties

ISO 1083 — 2018

Property	t <= 30 mm	30 < t <= 60 mm	60 < t <= 200 mm
Yield Strength (Rp0.2)	>= 350 MPa	>= 330 MPa	>= 320 MPa
Tensile Strength	>= 550 MPa	>= 520 MPa	>= 500 MPa
Elongation	>= 5 %	>= 4 %	>= 3 %

Separately cast, cast-on or side-by-side cast samples

Values apply to sand moulds or moulds of comparable thermal behaviour

alternative processes are subject to amendments agreed in the order.

Elongation: Elongation values determined from L0 = 5 d

Elongation: other gauge lengths see 9.1 and Annex B.

ISO 1083 — 2018

Informative

Property	t <= 30 mm	30 < t <= 60 mm	60 < t <= 200 mm
Yield Strength (Rp0.2)	>= 330 MPa	>= 310 MPa	>= 290 MPa
Tensile Strength	>= 530 MPa	>= 500 MPa	>= 450 MPa
Elongation	>= 4 %	>= 3 %	>= 2 %

test pieces machined from samples cut from castings

Informative reference value

not an acceptance requirement

Elongation: For elongation results, the reference gauge length is L0 = 5 d.

ISO 1083 — 2018

Informative

Property	Value
Shear Strength	500 MPa
Compressive Strength	840 MPa

Room temperature unless otherwise specified.

Informative reference value

not an acceptance requirement

Additional Mechanical Properties

ISO 1083 — 2018

Other Mechanical Properties

Informative

Property	Value
Torsional Strength	500 MPa

Room temperature unless otherwise specified.

Informative reference value

not an acceptance requirement

Welding Conditions

Not Available

Applications

Ductile iron ISO1083/JS/550-5 belongs to the spheroidal graphite iron casting family. In this casting family, components include pump and valve bodies, bearing housings, cover plates and parts for power transmission. Manufacturers supply such castings for agricultural equipment, vehicle assemblies and flow-control machinery.

Last Updated: 2026-11-16

Casting Quality Industrial

As a professional manufacturer in China, We Casting Quality focus on Metal Parts OEM industry, and provide solutions and services in Metal Casting field as following:

Sand Casting

Investment Casting, Lost Wax process

Shell Casting

Lost Form Casting

Permanent Mold Casting

CNC Machining

CAD Design

Tools/Mold Design

Material Supplied

Cast Iron Castings (Grey Iron, Malleable Iron, Ductile Iron)

Carbon Steel and Alloy Steel Castings

Stainless Steel and Duplex Stainless Steel Castings

Aluminum Castings

Bronze and Brass Castings

Titanium and Cobalt Alloy Castings

What We Can Do

Design Ability

Our engineers will help you to improve the designs based on casting technology, then The simulation software will be processed to verify the casting pouring system. Pro/E, Solidworks, AutoCAD and ProCast are available in Casting Quality Industrial.

Saving Cost

Some manufacture processes may lead high cost. We will analyses the designs and advise the suitable methods to our customers. The best solution will be adopted.

Quality Control

From the raw material selecting to bulk production processing, all procedures will follow PPAP program if necessary. The certificates will be provided including chemistry, hardness, mechanical property or NDT testing.

Production Capacity

The max iron/steel castings can reach 30tons in weight, meanwhile the minus casting is around 1gram only.

We also have prototyping and 3D scanning ability for sample plan.

Logistic Service

The products will be delivered directly to customer’s workshop, which will save plenty of work for clients.

Contact with Us Immediately:

Mark Wang

Email: mark@castingquality.com

WhatsApp: +861396488078

Website: www.castingquality.com

CASTING QUALITY