

Qingdao Casting Quality Industrial Co., Ltd.

International Standard

Prossional Suppler of Casting Part

Our manufacture processes: Sand Casting, Resin Sand Casting Investment Casting, Lost Wax Casting or Precision Casting Lost foam casting Die casting. CNC Machining.

The material included: cast gray iron, ductile iron, carbon steel, stainless steel, malleable iron ,brass alloy and aluminum alloy.

We serve and supply parts, components and products to wide varieties of industries as follow:

- 1. Valve fittings(valve body, wheel, disc, bonnet and others)
- 2. Pump Parts (Body, impeller and others)
- 3. Fastener (Bolt, nut, stud and gasket)
- 4. Automobile/ Motorcycle (drum, ...)
- 5. Pipe Fittings(malleable iron fittings, threaded stainless steel fittings, ductile iron fittings and others)
- 6. Steel anchor products.
- 7. Food Processing.
- 8. Computer & communication Hardware.
- 9. Sporting Equipment.

Tel: +86 532 82972967 Fax: +86 532 82972913



Qingdao Casting Quality Industrial Co., Limited

Tel: +86-532-82972967 www.castingquality.com Fax: +86-532-82972913 mark@castingquality.com

If you want to know the details, pls contact with us by email.

All the standard, such as ASTM, BS, ISO, DIN and other international standards, are from internet, only for study and investigation usage, don't use to business field.

Thanks for your visiting!

Casting Quality Industrial.









Designation: A 995/A 995M - 98 (Reapproved 2003)

Standard Specification for Castings, Austenitic-Ferritic (Duplex) Stainless Steel, for Pressure-Containing Parts¹

This standard is issued under the fixed designation A 995/A 995M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers austenitic-ferritic (duplex) stainless steel castings for valves, flanges, fittings, and other pressure-containing parts.

1.2 The duplex stainless steels offer a combination of enhanced mechanical properties and corrosion resistance when properly balanced in composition and properly heat treated. Ferrite levels are not specified, but these grades will develop a range of approximately 30 to 60 % ferrite with the balance austenite. It is the responsibility of the purchaser to determine which grade shall be furnished depending on design and service conditions, mechanical properties, and corrosionresistant characteristics.

NOTE 1—Because of the possibility of precipitation of embrittling phases, the grades included in this specification are not recommended for service at temperatures above 600°F [315°C].

1.3 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

2. Referenced Documents

2.1 ASTM Standards:

- A 488/A 488M Practice for Steel Castings, Welding, Qualification of Procedures and Personnel²
- A 703/A 703M Specification for Steel Castings, General Requirements, for Pressure-Containing Parts²
- E 125 Reference Photographs for Magnetic Particle Indications on Ferrous Castings³
- E 165 Test Method for Liquid Penetrant Examination³
- E 562 Test Method for Determining Volume Fraction by

TABLE 1	Heat	Treatment	Requirements
---------	------	-----------	--------------

Grade	Heat Treatment
1B	Heat to 1900°F [1040°C] minimum, hold for sufficient time to heat casting uniformly to temperature, quench in water or rapid cool by other means.
2A	Heat to 2050°F [1120°C] minimum, hold for sufficient time to heat casting uniformly to temperature, quench in water or rapid cool by other means.
3A	Heat to 1950°F [1070°C] minimum, hold for sufficient time to heat casting uniformly to temperature, quench in water or rapid cool by other means.
4A	Heat to 2050°F [1120°C] minimum for sufficient time to heat casting uniformly to temperature and water quench, or the casting may be furnace cooled to 1850°F [1010°C] minimum, hold for 15 min minimum and then water quench. A rapid cool by other means may be employed in lieu of water quench.
5A	Heat to 2050°F [1120°C] minimum, hold for sufficient time to heat casting to temperature, furnace cool to 1910°F [1045°C] minimum, quench in water or rapid cool by other means.
6A	Heat to 2010°F [1100°C] minimum, hold for sufficient time to heat casting uniformly to temperature, quench in water or cool rapidly by other means.

Systematic Manual Point Count⁴

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *duplex stainless steel*—an iron-chromium-nickelmolybdenum alloy which when properly heat treated consists of approximately 30 to 60 % ferrite with the balance austenite.

4. General Conditions for Delivery

4.1 Material furnished to this specification shall conform to the applicable requirements of Specification A 703/A 703M, including the supplementary requirements that are indicated on the purchaser order. Failure to comply with the general requirements of Specification A 703/A 703M constitutes nonconformance with this specification. In case of conflict between the requirements of the specification and Specification A 703/A 703M, this specification shall prevail.

5. Ordering Information

5.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved April 10, 2003. Published April 2003. Originally approved in 1998. Last previous edition approved in 1998 as A 995 – 98.

² Annual Book of ASTM Standards, Vol 01.02.

³ Annual Book of ASTM Standards, Vol 03.03.

⁴ Annual Book of ASTM Standards, Vol 03.01.