



Abrasion-Resistant Cast Iron ASTM A532 Class I type C

Ni-Cr-GB is a popular abrasion resistant cast iron in ASTM A532 standard class I type C; it is one type of White Iron.

Casting Methods in Casting Quality Industrial:

- Sand Casting
- Shell Casting

Equivalent Abrasion-Resistant Cast Iron Grade:

EN 12513 Grade EN-GJN-HB510 EN 5.5604
DIN 1695 Grade G-X 330 NiCr4 2 (DIN 0.9625)

Reference Casting Standards:

ASTM A532 Standard Specification for Abrasion-Resistant Cast Irons

ASTM A532 Class I type C Designation Ni-Cr-GB chemistry requirement:

www.castingquality.com

Standard	ASTM A532
Class	I
Type	C
Designation	Ni-Cr-GB
Carbon %	2.5-3.7
Manganese %	2.0 max
Silicon %	0.8 max
Nickel %	4.0 max
Chromium %	1.0-2.5
Molybdenum %	1.0 max
Copper %	-
Phosphorus %	0.30 max
Sulfur %	0.15 max



ASTM A532 Class I type C Designation Ni-Cr-GB Mechanical Property:

No requirement about tensile/yield and elongation. www.castingquality.com

ASTM A532 Class I type C Designation Ni-Cr-GB Hardness Requirements:

Standard	ASTM A532
Class	I



Type	C	
Designation	Ni-Cr-GB	
As Cast or As cast and Stress relieved	550HB/53HRC/600HV	
Hardened or Hardened and Stress Relieved	Level 1	600HB/56HRC/660HV
	Level 2	650HB/59HRC/715HV
Chill Cast, min	600HB/56GB/660HV	
Softened, max	400HB/41HC/430HV	

www.castingquality.com

ASTM A532 Class I type C Designation Ni-Cr-GB Heat treatment process

It will be up to the hardness requirement: as Cast, as Cast and Stress relieved, Hardened, Hardened and stress relieved, Softened for machining. www.castingquality.com

ASTM A532 Class I type C Designation Ni-Cr-GB Typical Casting Application:

- Pump industry.
- Mining industry, crusher liner, chute liner.
- Oil or recycling.

What is White Iron?

When white iron solidifies, virtually all the carbon appears in the form of carbides, White irons are hard and brittle, and they break with a white fracture. These irons are usually alloyed with Chromium and Nickel. The hardness is in the range of 500 to 600 BHN, the specific alloying that is required in a function of section size and application; there must be coordination between designer and foundry. These irons exhibit outstanding wear resistance and are used extensively in the mining industry for ball mill shell liners, balls, impellers, and slurry pumps. www.castingquality.com